



# WP7-101 Universal Roof Sealing

LIQUID MS POLYMER SEALER

- ✓ 100% waterproof and UV stable from 1 mm.
- ✓ Good adhesion to EPDM, tiles, metal roof materials.
- ✓ Durable waterproof and windproof, even in difficult places.
- ✓ Permanently flexible and walkable.

## Technical Info

- Base: 1K MS Hybrid polymer.
- Colour: black.
- Odor: odorless.
- Curing: cross-linking by reaction with air humidity.
- Consistency: pasta.
- Relative density: 1,45.
- Processing temperature: between +5°C and +35°C.
- Temperature resistance: from -40°C to +90°C.
- Skin formation: 1 hour.
- Curing:
  - after 24 hours: > 2 mm.
  - after 72 hours: > 4 mm.
- Shrinkage (DIN EN ISO 10563): ≤ 4%.
- Hardness (Shore A, EN 53505): 35.
- Tensile strength (EN 53504 S2): 1.9 N/mm<sup>2</sup>.
- E-modulus (EN 53504 S2): 1,4 N / mm<sup>2</sup>.
- Elongation at break (EN 53504 S2): +/- 300%.
- Shelf life: 12 months, in closed original packaging, dry, cool and frost-free.
- Safety measures: please consult the safety data sheet.

## Packing

WP7-101 Universal Roof Sealing - cartridge  
310ml

602450000

## Product

### Characteristics

Universal Roof Sealing is a liquid MS hybrid polymer that is easy to spread and cures to a waterproof sealing membrane with a very long life span. Universal Roof Sealing is also suitable for repair, finishing and renovation of medium-sized roofs that can be applied horizontally and vertically on most roof and building materials. Can also be applied on a slightly damp surface and is rain resistant after 2 hours.

### Applications

Roof sealing and renovation.  
Sealing of roof details such as conduits, connections, transitions, edges and sides.  
Renovation of roof elements and small flat roofs.  
Repair of leaks in EPDM foil, lead flashing, zinc and copper work.  
Protection of underground garden wood.

WP7-101 Universal Roof Sealing - can 750ml	602460000
WP7-101 Universal Roof Sealing - bucket 4L	602470000

## Use

- Apply on a clean and stable surface, also suitable to apply on slightly damp surfaces. Reinforce fragile surfaces, connections, seams and corners with fiberglass mesh. Large areas (> 4 m<sup>2</sup>) should be reinforced with Fiberglass reinforcement mesh.
- Apply with a brush or spatula, one layer a minimum of 1 mm thickness should be applied.
- Clean tools immediately with Tec7 Cleaner and your hands with Powerwipes.

Test the adhesion on EPDM and plastics. Discoloration and / or loss of adhesion can occur on bituminous materials, but it can be applied to slate-treated roofing. Not suitable for permanent immersion.

Consumption for 1mm thickness: 1 liter / m<sup>2</sup> . Consumption varies according to the roughness of the substrate.

