



# **Poxy Primer**

SUBSTRATE STRENGTHENER / BONDING PRIMER

- Improves and strengthens weak and powdery surfaces
- Protects iron and steel against rust, fixes loose rust particles
- Bonding primer for concrete rot repairs
- Mixing ratio 1:1

## **Technical Info**

- Composition: epoxy resin, hardener and solvent.
- · Colour: transparent yellow.
- Specific weight (mixture): 1 +/- 0.1 kg/dm<sup>3</sup>.
- Adhesion:
- Good adhesion to most building materials such as wood, stone, natural stone, concrete, ...
- Bond strength to metal: 2N/mm<sup>2</sup>.
- Temperature resistance: min. -30°C / max. +60°C / temporarily up to 110°C.
- Processing time: after mixing at +20°C: 30 minutes. Higher temperatures accelerate curing and lower temperatures slow down curing.
- Processing temperature: between +5°C and +30°C.
- Drying time: dust dry and can be walked on after 12 hours.
- Chemical resistance after seven days:
- Resists water, salt water, dilute acids and bases, salts, oils, fuels, urine, fertilisers and most solvents.
- Shelf life: minimum 12 months in closed packaging store frost-free.
- Safety measures: Please consult the safety data sheet.

## Packing

Poxy Primer - 1kg

631213000

## Product

#### Characteristics

- · 2-component epoxy primer
- High penetration into porous substrates
- Strengthens weak surfaces through impregnation
- Fixes powdery surfaces
- Neutralises rust
- Suitable for indoor and outdoor use

#### Applications

- Concrete rust repair: neutralises rust on rebar + bonding primer for Floor Fix / Wall Fix.
- Fixing of powdery surfaces for painting / bonding.
- Reinforcing weak substrates for bonding: cellular concrete, plaster, gypsum board, plasterboard, natural stone, weathered concrete, etc.
- Bonding primer for bonding on concrete, natural stone, ...
- Reinforcing façade bricks with suspended bonding under steel beams.
- Protects concrete and facade bricks against the effects of salts, manure, urine, etc.



Industrielaan 5B - B-2250 Olen - Belgium | Tel: +32 14 85 97 37 | info@tec7.com

Novatech International INV produces all information with the utmost care but cannot give any guarantees as to its nature, content and/or use. The company does not accept any liability for direct or indirect damage caused by the contents of the information included. All images included are for indicative purposes only. No rights may be derived from them. None of the published data may be copied, stored in an automated database and/or made public, in any form or manner, without the explicit prior written consent of Novatech International NV.

ustrielaan 5B - B-2250 Olen - Belginm | lei: +32 14 85 97 37 | Inio@let7.com

Novatech International NV produces all information with the utmost care but cannot give any guarantees as to its nature, content and/or use. The company does not accept any liability for direct or indirect damage caused by the contents of the information included. All images included are for indicative purposes only. No rights may be derived from them. None of the published data may be copied, stored in an automated database and/or made public, in any form or manner, without the explicit prior written consent of Novatech International NV

### Use

#### Preparation

- Minimum processing temperature: +5°C.
- Apply to a clean, completely dry surface.
- After mixing, processable for +/- 30 minutes at temperatures of +20°C. At high temperatures, the components can be cooled for a longer processing time.
- Pour the hardener (Component B, plastic bottle) completely into the resin (Component A, can), or use the measuring cup provided for a 1:1 mixing ratio.
- Mix very thoroughly until both components are completely mixed.

#### Processing

- After mixing, apply immediately with a brush or roller.
- On highly absorbent surfaces: apply a second coat after +/- 1 hour or longer.
- The Tec7 adhesives and sealants can be applied wet-on-wet on Poxy Primer.
- Protect from moisture and rain for 24 hours after application.
- Can be walked on and dust dry after +/- 12 hours at +20°C. Chemically resistant after 7 days at +20°C.
- Clean tools with Spray & PUR Cleaner.
- Can be painted over with most varnishes and paints.

#### Use

- Depending on the porosity of the substrate:
  - First coat: 150–300 ml/m<sup>2</sup>.
  - Second coat: 250 ml/m<sup>2</sup>.

